



CERTIFICATE OF ANALYSIS
CCRL Calibration Standard
Portland Cement 220

This material is a calibration standard and is not a certified reference material. This material is intended primarily for use in calibrating instrumental equipment used in the analysis of cement and similar materials. A unit of CCRL Calibration Standard – Portland Cement 220 consists of a vial containing approximately 30 g of portland cement passing a 150 μm sieve. Portland Cement 220 is an ASTM C150 cement meeting Type I specifications. This cement contains limestone additions and inorganic processing additions.

Certificate Values: Values for eighteen constituents in CCRL Calibration Standard – Portland Cement 220 are listed in Table 1. The values in Table 1 are consensus values derived from CCRL Portland Cement Proficiency Sample 220.

Expiration of Certificate and Stability: The certificate of this calibration standard is valid until 1 January 2026 provided the standard is handled and stored in accordance with the instructions given. This material is considered to be stable during the period covered by this certificate within the limitations given in “Instructions for Use”.

INSTRUCTIONS FOR USE

Cement powder is hygroscopic and will react with moisture changing the chemical composition. Each unit of the calibration standard is stored in a sealed pouch during preparation to prevent moisture uptake. The unit should be left in the sealed pouch until just before it is needed in the laboratory. After the vial is removed from the pouch, the vial should be stored in its original container, recapped tightly, and stored in a desiccator immediately after use.

Reporting: For all constituents, values are reported as mass fractions on as-received basis. The constituents are expressed as the chemical forms and in the order given in ASTM C 114-18, Table 1.

Table 1. Values for CCRL Calibration Standard 220 – Portland Cement

Constituent	Value %	Expanded ^(a) Uncertainty %
SiO ₂	19.91	0.005
Al ₂ O ₃	4.76	0.003
Fe ₂ O ₃	2.65	0.002
CaO	61.70	0.007
MgO	3.38	0.003
SO ₃	4.27	0.003
LOI	0.93	0.002
Na ₂ O	0.283	0.002
K ₂ O	1.074	0.002
SrO	0.272	0.002
TiO ₂	0.21	0.001
P ₂ O ₅	0.170	0.001
ZnO	0.129	0.002
Mn ₂ O ₃	0.147	0.001
Cl	0.005	0.001
IR	0.22	0.003
Free Calcium Oxide ^(b)	0.80	0.005
CO ₂	0.32	0.004
Limestone Content	1.0	0.007
Cr ₂ O ₃	0.028	0.001
^(a) The uncertainty listed was calculated as a 95% confidence interval from the standard error of the mean (sd / \sqrt{n}) with a coverage factor (k) of 2.0. ^(b) Value consists of free CaO and, if present, free Ca(OH) ₂ .		

Cooperating Laboratories: Analytical determinations for certificate values of this calibration standard were performed by the participating laboratories of the Cement and Concrete Reference Laboratory proficiency sample program. The number of participants involved these determinations varied from 91 to 218 depending upon which constituent was being determined.