

CCRL Portland 233		
Oxides	Limestone	Inorganic processing addition
SiO ₂	13.8	0.0
Al ₂ O ₃	5.2	0.0
Fe ₂ O ₃	2.0	0.0
CaO	45.4	0.0
SO ₃	1.0	0.0
CO ₂	35.6	0.0

Ingredient	% by mass
Inorganic processing addition	0.0

CCRL Portland 234		
Oxides	Limestone	Inorganic processing addition
SiO ₂	3.7	0.0
Al ₂ O ₃	1.9	0.0
Fe ₂ O ₃	0.6	0.0
CaO	51.5	0.0
SO ₃	0.6	0.0
CO ₂	41.3	0.0

Ingredient	% by mass
Inorganic processing addition	0.0